



IST & AST SEALANT TAPES

Wet Sealant Compatibility Chart

TEST DATA

Manufacturer:

EMSEAL JOINT SYSTEMS, LTD.

23 Bridle Lane, Suite 3

Westborough, MA 01581-2603

TOLL FREE: 800-526-8365 PH: 508-836-0280 FX: 508-836-0281

EMSEAL CORPORATION

84 Brydon Drive

Rexdale, ON, Canada M9W 4N6

TOLL FREE: 866-436-7325 PH: 416-740-2090 FX: 416-740-0233

Manufacturer / Product	Compatibility	Adhesion to Foam
Bostik Construction Products		Yes
Chem-Calk 500	Yes	Yes
Chem-Calk 550	Yes	Yes
Chem-Calk 900	Yes	
Dow Corning		
Dow 790	Yes	Yes
Dow 795	Yes	No
Dow 999	Yes	Yes
General Electric		
Silpruf	Yes	Yes
Gesil N	Yes	Yes
SCS 1200	Yes	Yes
Pecora Corporation		
Dynatrol - I	Yes	Yes
Dynatrol - II	Yes	Yes
Dynatred	Yes	Yes
Sika Corporation		
Sikaflex - 15LM	Yes	Yes
Sikaflex - 2CNS	Yes	Yes
Sonneborn Building Products		
NP1	Not Tested	Yes
NP2	Not Tested	Yes
Omniseal	Not Tested	Yes
Omniplus	Not Tested	Yes
Tremco		
Butyl	Yes	Yes
Dymeric	Yes	Yes
Dymonic	No	Yes
Mono	Yes	Yes
Proglaze	No	Yes
THC 900	Yes	Yes

GENERAL NOTE: Light colored sealants which are installed in direct contact with AST will become dri colored (darkened) over time. Generally IST is chosen in applications where direct application of a liquid sealant is intended.

Individual test reports from sealant manufacturer are available